



ELASTI MULTI SPECJAL 104

Elastic, universal adhesive

Areas of application:

Intended for applying all types of wall and floor ceramic tiles (ceramics, terracotta, clinker, gres), also the large-format ones, on rigid and deforming indoor and outdoor groundworks

Indoor and outdoor use

Can be also used for applying natural stone tiles (with the exception of marble), after verifying their possible discoloring.

Intended for balconies and terraces, for humid rooms (bathrooms, kitchens, laundry rooms), to be applied on cement and anhydrite screed with floor heating. Suitable for applying reinforcing layer panels in thermal insulation systems.

Properties:

- Flexible
- Waterproof
- Freezeproof
- Universal
- Long open and correction time
- For demanding groundworks
- For floor heating systems
- C2TE class

Application procedure:



Technical data	
Item No.	314693
Packaging type	
Quantity per unit	25 kg
Unit per pallet	48 Stk./Pal.
Colour	grey
Granulation	0.5 mm
Consumption	1.4 kg/m ² /mm

More technical Details:

Classification as per EN 12004+A1: C2TE

Shelf life after mixing with water: 2 hours (at +20°C)

Tile application time after the application of adhesive on the groundwork: up to 30 minutes

Correction time: up to 20 minutes

Possibility of standing on the laid floor: after 24 hours

Possibility of pointing: after 48 hours

Water mixing ratio: 6.4 liters of water per 25 kg of dry mix

Maximum grout layer: up to 5 mm

Adhesion: $\geq 1,0 \text{ N/mm}^2$

Soluble chromium VI content: $\leq 0,0002\%$

Material base:

- Portland cement
- Modifying additives
- Mineral fillers
- Polymers



ELASTI MULTI SPECJAL 104

Elastic, universal adhesive

Surface:	<p>Remove all unstable grouts and coats. Plasters and cement screeds must be at least 4 weeks old, gypsum plasters and anhydrite screeds must be at least 2 weeks old. Grind and vacuum anhydrite screed. Concrete groundwork must be at least 6 months old.</p> <p>Level all groundwork irregularities with the 428 leveling grout. Irregular cement and concrete floor surfaces should be leveled with the RENOGRUNT 410, RENOGRUNT 411 or RENOGRUNT 412 self-leveling grout. Anhydrite screed should be leveled with SAMOPOZIOMUJĄCY PODKŁAD PODŁOGOWY 201.</p> <p>Clean all old, well-gripping ceramic tiles and oil wainscot and execute a contact layer using a class C2, S1 or S2 adhesive or the GRUNTOBET 310 primer. Remove all bituminous mass residues (left after removed parquets) from the groundwork.</p>
Types of substrate:	<p>Concrete, reinforced concrete: Prime with CONTACT GRUNT 307</p> <p>Gypsum, gypsum-lime, cement, cement-lime and lime cement: Prime with GRUNTOLIT-SG 302 or EXPERT 5</p> <p>Cement screed: Prime with GRUNTOLIT-W 301 or EXPERT 6</p> <p>Anhydrite screed: Grind, vacuum and prime with GRUNTOLIT-W 301</p> <p>Wallboards: Prime with GRUNTOLIT-W 301 or EXPERT 6</p> <p>Autoclaved aerated concrete elements: double prime with GRUNTOLIT -W 301</p> <p>Silicate blocks: Prime with GRUNTOLIT-W 301 or EXPERT 6</p> <p>Old ceramic tiles and oil wainscot: Prime with CONTACT GRUNT 307</p> <p>Liquid foil, polymer-cement sealants: Apply directly</p> <p>Reinforcing layer in the thermal insulation system: Apply directly</p>
Preparation:	<p>Pour the dry mix gradually to a container with a sufficient amount of clean, cool water. Mix manually or using a low-speed mixer to produce a homogeneous mass without lumps. Leave to mature for 5 minutes and mix again. The mass should be thick enough not to slide from a trowel when set at an angle.</p> <p>If there is a need to use a part of the packaging, the entire dry compound must be carefully stirred because during transport components could be separated.</p> <p>Do not mix the hardened grouting mixture again.</p>
Application procedure:	<p>Apply the grout on the groundwork using a toothed trowel.</p> <p>Apply the prepared mortar onto the steel trowel and firmly spread a thin layer across the bed using the straight edge. The next step is to apply a thicker mortar layer and spread it using the notched edge of the trowel at an angle of 45-60 degrees to the bed. The area covered with the mortar should be adjusted to the tiles laying abilities not to exceed the open drying time of the adhesive. It can be verified by touching the grout with a finger; if no adhesion occurs, the open drying time was exceeded and the grout should be removed from the surface and replaced with a fresh layer. The tiles should be laid by placing the second one as close to the first one and moving it to receive a joint of proper width. The tiles should not be wet before laying! Press tiles and if need be strike with a rubber hammer against the bed so that the adhesive will adhere to at least 70% of surface of a tile. Tiles bigger than 30x30 cm, all tiles laid outside and in permanently wet and intensively used places should be laid so that the adhesive will adhere to the entire tile surface. In order to meet these requirements the adhesive should be also applied to the entire back of the tile with a thin layer of equal thickness, covering the concavities and convexities.</p> <p>The joint width should be chosen based on the tile size. Internal floors adopt the following: minimum 2mm - at the tile side length up to 10 cm, 2-6mm - using tiles of 10-25cm, 4-8 mm - using tiles of 25-30 cm. Before the adhesive dries, the possible grout residue should be removed from the joints, and the tiles should be washed with water. For the external floors, depending on the tile colour and sunlight, the provided values should be increased by 50-80%. Before the adhesive dries, the possible grout residue should be removed from the joints, and the tiles should be washed with water. In case of clinker tiles, the floor should be coated with HYDROMUR-W 1010, but not sooner than 4 days after pointing. Facades exposed to precipitation should be protected from rainfall until the moment of impregnation.</p>



ELASTI MULTI SPECJAL 104

Elastic, universal adhesive

Application conditions:	Apply in temperatures from +5°C do +25°C. These temperatures apply to air, groundwork and product temperature. All groundworks should be load-bearing, tight, stable, cleared and, if necessary, primed with EXPERT 6 or GRUNTOLIT-W 301. Prime poor-quality groundworks with EXPERT 5 - deep-penetration primer. Smooth substrates that require increased adhesion are recommended to be primed with GRUNT CONTACT 307.
Instructions:	Avoid contact with skin and protect eyes. Detailed guidelines are included in the material safety data sheet.
Storage:	Up to 12 months from the date of manufacture, in dry places and in intact packaging
General information:	This product data sheet replaces all its previous versions. The information, included in this technical card, represents our current knowledge and practical experience. This is general information only which shall not obligate the manufacturer to take any responsibility either for workmanship or for the manner of use. For there may be differences and specific execution conditions. The product shall be applied in accordance with required technical knowledge and OHS rules. Avoid contact with skin and protect eyes. In case of contact with eyes, rinse them up with a large quantity of clean water and consult a doctor. It shall be recommended to use gloves, safety goggles and protective clothing.