



EXTERNAL GYPSUM FILLER 602

White cement finishing coat

Areas of application: Intended for manual execution of indoor and outdoor finishing coats on walls and ceilings. Suitable for executing perfectly smooth layers under paints or quality plasters on walls and ceilings with cement-lime plasters, gypsum plasters, etc., or on plasterboard surfaces. Can be used in rooms with air humidity above 70%.

Properties:

- Waterproof
- Frost-resistant
- High grip
- Ideally white
- Smooth surface
- For facades
- Vapor-permeable

Application procedure:



Technical data	
Item no.	12069
Packaging type	
Quantity per unit	25 kg
Unit per pallet	48 Pcs/pallet
Colour	White
Granulation	0 - 0.2 mm
Consumption	1 kg/m ² /mm
Drying time	from 24 to 48 hours
Application time	approx. 2 h
Layer thickness	≤ 5 mm
Soluble chromium VI content	≤ 0.0002 %
Amount of water required	approx. 10.5 l/bag
Reaction to fire	A1
Adhesion to (Concrete)	≥ 0.25 N/mm ²

The product conforms to: • EN 998-1

Material base:

- White Portland cement
- Dolomite
- Mineral fillers
- Additives

Surface: The groundwork must be cleaned and properly prepared. Symptoms of biological aggression should be eliminated. Reinforce all groundwork types, installation furrows and all other places prone to structural cracking with glass fiber mesh.

Types of substrate:

Cement-lime plaster: Prime with GRUNTOLIT-W 301 or EXPERT 6

Gipsputz: Prime with GRUNTOLIT-SG 302 or EXPERT 5

Gypsum plasterboards: Prime with GRUNTOLIT-SG 302 or EXPERT 5

Concrete, reinforced concrete: Prime with GRUNTOLIT-SG 302 or EXPERT 5



EXTERNAL GYPSUM FILLER 602

White cement finishing coat

Preparation:	<p>Pour the dry mix gradually to a container with a sufficient amount of clean, cool water, mixing manually or using a low-speed mixer to produce homogenous, lump-free mass. Leave to mature for 5 minutes, and then mix again.</p> <p>If necessary, depending on the conditions, slightly adjust the amount of water added.</p> <p>Do not mix the hardened grouting mixture again.</p>
Application procedure:	<p>After the finishing coat has dried, grind all surface irregularities with sandpaper or mesh</p> <p>Clean all surface inaccuracies of dust and re-apply the finishing coat</p>
Application conditions:	<p>Apply in temperatures from +5 °C to +25 °C, these temperature refer to air, groundwork and product temperature.</p> <p>Proceed to applying the finishing coat after all walls and concrete elements have settled, compressed and dried up. A groundwork for finishing coat should be fixed, hard and non-deforming.</p>
Instructions:	<p>Protect against frostbite, precipitation and excessive drying in the execution of works and during the drying period. The use of protective covers is recommended.</p>
Storage:	<p>Up to 12 months from the date of manufacture, in dry places and in intact packaging</p>
General information:	<p>This product data sheet replaces all its previous versions. The information, included in this technical card, represents our current knowledge and practical experience. This is general information only which shall not obligate the manufacturer to take any responsibility either for workmanship or for the manner of use. For there may be differences and specific execution conditions. The product shall be applied in accordance with required technical knowledge and OHS rules. Avoid contact with skin and protect eyes. In case of contact with eyes, rinse them up with a large quantity of clean water and consult a doctor. It shall be recommended to use gloves, safety goggles and protective clothing.</p> <p>All technical data is given for the temperature of 20 degrees Celsius. These temperatures apply to air, bed and embedded material.</p>