



# Fixit 203

Finish coat with hydraulic lime


**Areas of use:** Fixit 203 is a paint-ready mineral-based finish coat for indoor and outdoor use and is ideal for replicating historical structured plasterwork. Hydraulic plasters are particularly suitable substrates. Older base coats with poor strength may be reinforced by pretreating with Fixit 493 mineral Base Coat Stabilizer.

**Properties:**

- Historic plaster surface imitation possible, with a range of application techniques
- Hydrophilic and therefore with very good capillary active and water vapour diffusion properties
- For both indoor and outdoor use
- ECO certified

**Application procedure:**



Technical data	
Packaging type	
Unit per pallet	40 unit/pal.
Quantity per unit	25 kg/unit
Granulation	0 - 1 mm
Water addition rate	5 - 6 l/bag
Consumption	approx. 1.3 kg/m <sup>2</sup> /mm
Application time	90 - 120 min
Layer thickness	1 - 3 mm

**Composition:**

- Binding agent: hydraulic lime, white hydrated lime, white cement
- Aggregates: sand-lime with grain size 0 - 1 mm
- Additives: Water retention agents, air entraining agents

**Basics:** The general rules of building construction must be observed, in addition to the current notes published by the «Swiss Association of Painters and Plasterers SMGV», the recommendations SIA 242 «Rendering and Plastering» and the information in this technical data sheet.

**Application procedure:** Fixit 203 should be mixed with clean water by hand. Marble pit lime may be added to the mixing water to improve smoothness and increase the strength of the render. The substrate must be wetted in advance of application. The surface structure can be created using trowel strokes, jute-sack impressions, brush strokes, whitewash etc.

**Post-application treatment:** The freshly applied render should be protected from exposure to bad weather and direct sunshine. Provide shade, additional humidification, protection from driving rain and hail etc. as necessary.

**Storage:** Store in a dry place on wooden battens. Storage life min. 12 months. Binding properties may be affected if stored for longer.

**Certificates:**



**Origin:**





## Fixit 203

Finish coat with hydraulic lime

---

**Important note:**

Do not apply when the air or substrate temperature is below +5 °C.  
Allow the plaster to adequately carbonate before applying paint coats.  
Exception: lime paint may be applied "wet-on-wet".