



Fixit 211


Roughcast mortar with adhesive agent

Areas of use: Fixit 211 is a roughcast mortar with adhesive agent, and is a component of the Fixit Restoration Plaster system. It helps to improve the adhesion of the subsequent plaster layer. The substrate must be clean, dry and of adequate load-bearing capacity.

- Properties:**
- Machine compatible for economic renovations
 - Secure application due to adhesion promoter
 - Can be used as substrate for several base coats
 - ECO certified

Application procedure:



Technical data	
Packaging type	
Unit per pallet	40 unit/pal.
Quantity per unit	25 kg/unit
Granulation	0 - 3 mm
Water addition rate	approx. 5 l/bag
Consumption	approx. 3 kg/m ²
Application time	90 - 120 min
Dry bulk density	> 1,600 kg/m ³
Compressive strength (28 d)	≥ 20 N/mm ²
Pressure resistance (28 d)	≥ 5 N/mm ²

- Composition:**
- Binding agent: cement
 - Aggregates: crushed sand and quarry sand, grain size 0 - 3 mm
 - Additives: Water retention agents, air entraining agent, adhesion promoters

Basics: The general rules of building construction must be observed, in addition to the current notes published by the «Swiss Association of Painters and Plasterers SMGV», the recommendations in SIA 242 «Rendering and Plastering», SIA Note 2003 „Restoration Plasters and Resoration Plaster Systems“ as well as the information in the relevant technical data sheets.

Application procedure: Fixit 211 should be mixed with clean water and then applied in a thin but complete layer by hand or using a conventional plastering machine. Opacity: 50 – 100% of the surface.

Post-application treatment: In extreme weather conditions (in direct sunshine, rapidly changing temperatures etc.) measures must be taken to protect the freshly applied rendering.

Storage: Store in a dry place on wooden battens. Storage life min. 6 months. Binding properties may be affected if stored for longer.

Certificates:



Origin:





Fixit 211

Roughcast mortar with adhesive agent

Important note:

Do not apply when the air or substrate temperature is below +5 °C.

If intended for use as a component in the Fixit Fixit Restoration Plaster system, its suitability must be ascertained in advance (see System description)