



Fixit 763

Lime cement render

Areas of use: Fixit 763 is a final rendering for applying to exterior cement or lime based surfaces. The substrate must be clean and of adequate loadbearing capacity. The prior application of Fixit 475 Primer for mineral plasters is recommended.

Properties:

- Mineral-based and biocide-free
- Diverse structures possible
- Historically important plaster patterns
- On cement and limestone substrates
- Range of grain sizes

Application procedure:



Technical data					
Packaging type					
Unit per pallet	40 unit/pal.				
Quantity per unit	25 kg/unit				
Granulation	1 mm	1.5 mm	2 mm	3 - 4 mm	5 - 6 mm
dashed	Full abrasion				
Water addition rate	6 - 8.5 l/bag				
Consumption	approx. 2 kg/m ²	approx. 2.4 kg/m ²	approx. 2.7 kg/m ²	approx. 5 kg/m ²	approx. 6.5 kg/m ²
Consumption	approx. 2 kg/m ²	approx. 2,4 kg/m ²	approx. 2,7 kg/m ²	approx. 5 kg/m ²	approx. 6,5 kg/m ²
Application time	approx. 90 min				

Composition:

- Binder: white lime, portland cement
- Aggregates: limestone sands
- Additives: Water retention agents, air entraining agents

Basics: The general rules of building construction must be observed, in addition to the current notes published by the «Swiss Association of Painters and Plasterers SMGV», the recommendations SIA 242 «Rendering and Plastering» and the information in this technical data sheet.

Application procedure: Fixit 763 is mixed with clean water and applied by hand. With substrates which absorb water poorly, improve adhesion by adding to the mixing water approximately 1 L of Fixit 497 Plaster and Mortar Emulsion per sack .

Post-application treatment: The freshly applied render should be protected from exposure to bad weather and direct sunshine. Provide shade, additional humidification, protection from driving rain and hail etc. as necessary.

Storage: Store in a dry place on wooden battens. Storage life min. 6 months. Binding properties may be affected if stored for longer.

Further notes:



Important note: Do not apply when the air or substrate temperature is below +5 °C.

Drying

The setting time of Fixit 763 depends on the temperature and relative humidity of the surroundings. Low temperatures and/or high humidity delay the drying process. After about 10 days at + 20° C air and substrate temperature, and 65 % relative humidity, painting may begin. Basically, the Fixit 763 may only be painted after sufficient time has elapsed to allow complete carbonation to occur.



Fixit 763

Lime cement render

General provisions:

This technical information sheet replaces all previous versions of the information sheet for this product. The details in this technical information sheet were drawn up carefully and conscientiously based on the current state of knowledge and experience and refer to the usual purpose of use. The information is provided without any warranties regarding accuracy and completeness and any and all liability is excluded. It also does not establish any contractual legal relationship with or subsidiary obligation of Fixit AG. Customers and users are personally responsible for checking that the products are suitable for the intended purpose of use. The latest versions of our technical information sheets are available on our website or can be ordered from the competent branch.